

TH 976

Silicone Thermal Grease

Description

TH 976 is a white, highly filled silicone system suitable for the screen printing process and thermal dissipation of electronic devices. This one part system is designed to be non-curable. It has stable pot life and long shelf life even at room temperature of 25°C. It has relatively low viscosity for faster dispense from syringes.

Applications

Heat dissipation from electronic components.

Guidelines for Use

1. Thaw the silicone to room temperature (25°C) before use.
2. Dispense the silicone by using a syringe.
3. Wipe off any excess material with a piece of dry cloth or tissue. Further cleaning may be achieved by wiping with cloth wetted with iso-propanol.

Properties

Property	Test Method	Unit	Typical Value
Chemical type	-	-	Silicone
Appearance	Pen 10	-	White liquid
Shelf life, -20°C	Pen 26	Month	6
Specific gravity, 25°C	Pen 14	-	2.1
Viscosity, Brookfield Cap 2000+, 25°C	Pen 44	cP	20,000
Thermal conductivity	ASTM D5470	W/mK	3.0

Storage

Tightly close original container of unused product. Store in a cool and dark place.

Packaging & Dimension

- 30 ml EFD syringe
- 300 ml plastic jar
- 1 kg plastic pail

Environment, Health & Safety

This product is RoHS compliant. It does not contain any known carcinogenic, mutagenic or teratogenic components.

Contact Information

Penchem Technologies Sdn Bhd
(767120-A), 1015, Jalan Perindustrian Bukit Minyak 7, 14100 Penang, Malaysia
T: +604-501 5976, 77, 78, 79
E: enquiry@penchem.com
W: www.penchem.com

Revision 4: 12-Jul-18.NN