

CT 682

Acrylic Conformal Coat

Description

CT 682 is a clear, colorless acrylic system suitable for coating and protection of electronic components and printed circuit boards. This conformal coat provides excellent moisture and environmental protection. It is a one-component, solvent-based, air-dried coating system. It has a fluorescent agent for easy inspection under UV light. It is recommended for coating and protection of electronic parts, most plastics, ceramics and metals.

Applications

Water resistant conformal coat for electronic components and printed circuit boards

Guidelines for Use

1. Make sure the surfaces to be coated are free from dust and grease.
2. The liquid conformal coat may be applied by brushing, spraying or dipping.
3. Sufficient drying may be achieved by leaving at room overnight (16 hours). Complete drying may take several days. Faster drying may be achieved by heating in a convection oven, eg. 30 minutes at 80°C.
4. Wipe off any excess coating material with a piece of dry cloth or tissue. Further cleaning may be performed with tissue wetted with iso-propanol.
5. Typical tack-free time for thin films is less than 30minutes.

Properties

| Property | Test Method | Unit | Typical Value |
|----------------------------------|-------------|---------|---------------|
| Chemical type | | | Acrylic |
| Appearance | Pen 10 | | Clear liquid |
| Mix ratio, by weight | | | One component |
| Shelf life, 25°C | Pen 26 | Month | 12 |
| Viscosity, Brookfield RVT, 25°C | Pen 11 | cP | 266 |
| Hardness, 80 °C for 1 hr | Pen 29 | Shore D | 50 |
| Dielectric constant, 1MHz, 25 °C | Pen 21 | | 2.5 |
| Solids content | Pen 19 | % | 40 |
| Glass transition temperature | | °C | 85 |

Recommended Cure

| Temperature | Cure Time |
|-------------|-----------|
| 25°C | 16 hr |
| 80°C | 30 min |

Storage

This material is inflammable. Store unused material in an air-tight container away from high temperatures and ignition sources.

Packaging

- 1 kg can

Environment, Health & Safety

This product is RoHS compliant. It does not contain any known carcinogenic, mutagenic or teratogenic components.

Contact Information

Penchem Technologies Sdn Bhd
(767120-A), 1015, Jalan Perindustrian Bukit Minyak 7, 14100 Penang, Malaysia
T: +604-501 5976, 77, 78, 79
E: enquiry@penchem.com
W: www.penchem.com

Revision 6: 11-Jul-18.NN